



Concrete Admixtures and Fiber

IMISEAL-G

30% Solids Acrylic Solvent Based Clear Sealer

PRODUCT DESCRIPTION

IMISEAL-G is a specially formulated 30% solids, solvent based clear sealer for exposed aggregate, architectural concrete and terrazzo. It is non-yellowing and abrasion resistant. **IMISEAL-G** provides a glossy finish and forms a strong impermeable seal.

USES

- For sealing of concrete surfaces that will be subject to abrasion and spillage of common chemicals
- For sealing of exposed aggregate concrete surfaces, enhancing the appearance of the exposed aggregate
- Applied as a protective seal coat on terrazzo surfaces.
- Provides protection against abrasion and spillage and provides a rich luster to terrazzo surfaces
- To protect concrete surfaces against discoloration, dust, air pollutants and spillage of common chemicals
- Complies with ASTM C-309, Type 1

TECHNICAL INFORMATION

IMISEAL-G is a clear, colorless solution that, when applied, will provide a glossy protective shield. It is UV resistant and will not turn yellow upon exposure to sunlight. The protective shield will resist attack from aggressive chemicals, thus providing protection to the concrete surface. **IMISEAL-G** is compatible with and allows adhesion to most paints and tile adhesives. Field tests are advised to substantiate the compatibility of materials.

INTERNATIONAL MATERIALS INDUSTRIES, L.L.C.

2800 N. Johnson St.* New Orleans, Louisiana 70117 * PHONE: (504) 267-3344 * Fax: (504) 267-3345

The information herein is to assist customers in determining whether our products are suitable for their applications. Our products are intended for sale to industrial and commercial customers. We request that customers inspect and test our products before use and satisfy themselves as to contents and suitability, nothing herein shall constitute a warranty, express or implied, including any warranty of merchantability or fitness, nor is protection from any law or patent to be inferred. All patent rights are reserved. The exclusive remedy for all proven claims is replacement of our materials and in no event shall we be liable for special, incidental or consequential damages.

INSTALLATION

Preparatory Work

New Concrete - IMISEAL-G should be applied to new concrete after three or five days of being placed depending on the weather conditions.

Old Concrete - IMISEAL-G should be applied only after all stains have been removed. The concrete should be thoroughly dry before applying IMISEAL-G .

Method of Installation - IMISEAL -G may be applied to the surface by spraying or with a brush or short-nap mohair roller.

Coverage - One gallon of IMISEAL-G will cover from 200 to 600 square feet (19 - 56 sq. meters), depending upon the surface texture and specification requirements.

LIMITATIONS

IMISEAL-G should not be used on surfaces that will receive cementitious coatings. Liquid floor hardeners will not penetrate concrete slabs treated with IMISEAL-G